



储能用铅酸蓄电池

LEAD-ACID STORAGE BATTERIES USED FOR ENERGY STORAGE JYHY121000(12V100AH)

JYHY121000 (12V100AH) lead-acid storage batteries used for energy storage, they are made with advanced technology which has long service life, low-self-discharge rate, particularly suitable for deep cycle usage and so on, applied for solar and windy power systems such as solar street lights、solar off-grid power station、windy power farms .etc.

JYHY121000 (12V100AH) 储能用铅酸蓄电池采用先进制造技术，具有使用寿命长、自放电率低、特别适合深循环使用等特点，适用于太阳能路灯、太阳能离网电站、风力发电场等太阳能、风能发电系统。

Specification 基本特性

- ◆UL、CE-recognized component.产品通过UL、CE认证
- ◆Can be mounted in any orientation.除倒置外，可任意方向安装使用
- ◆Computer designed lead,calcium tin alloy grid for high power density.采用高锡铅钙多元合金板栅
- ◆Long service life,float or cyclic applications,float designed to use for 5-8 years.浮充、循环使用寿命长，浮充使用设计寿命可达到5-8年
- ◆Maintenance-free operation 免维护使用
- ◆Absorbent Glass Mat(AGM) technology for efficient gas recombination of up to 99%,low gas escape .采用AGM隔板高吸收技术，气体复合率可以达到99%，极少气体析出
- ◆SPECIFICATION 参数
Nominal voltage 额定电压12V
Number of cell 单格数.....6
Approx.weight 净重.....29KG

Performance Characteristics 性能参数

额定容量 Capacity 77° F (25° C)	10小时率 hour rate(10A, 10.5V)	100Ah
	5小时率 hour rate (17A,10.5V)	85Ah
	1小时率 hour rate (60A, 9.6V)	60Ah
内阻 Internal Resistance Approx.4mΩ		
适用温度范围 Operating TemperatueRange	Discharge:-20℃-60℃ 放电(温度范围)	
	Charge: 0℃-50℃ 充电(温度范围)	
	Storage;-20℃-60℃ 储存(温度范围)	
标准适用温度范围 Normal Operating Temperature Range:25°C±5°C		
自放电 Self-Discharge	该电池在常温25摄氏度的环境下至少可以储存12个月,电池在使用之前先充电,储存时周围环境温度越高,它的储存周期越短。 the battery can be stored for more than 12 months at 25°C,please charge batteries before using .For higher temperature,the time interval will be shorter.	
每月自放电率≤1.3% Self discharge rate ≤ 1.3% monthly		
最大放电电流 Max,discharge current (25° C) : 650A(5S)		
恒压充电 Charger (Constant Voltage)	浮充使用 Float charging Voltage	13.6 ~ 13.8V (25°C)
	循环使用 Cycle Use	14.6 ~ 14.8V (25°C)
建议最大充电电流 Recommended Maximum Current Limit: 30A		

产品尺寸(单位:毫米)Dimensions (Unit:mm) :327(L)×172(W)×225(H)

端子terminal

导线wire:
长度length: 1800mm
线径 the cross-sectional area of copper wire:4mm²

电池结构Battery Construction

元件 Component	正极板 positive plate	负极板 negative plate	胶壳 Container	胶盖 Cover	安全阀 Safety valve	端子/导线 Terminal/wire	隔板 Separator
原料 Raw material	二氧化铅 Lead dioxide	铅 Lead	ABS	ABS	橡胶 Rubber	铜 Copper	玻璃纤维 Fiberglass

恒流放电特性Constant current discharge characteristicsUnit:A(25℃)

F. V/TIME	10min	15min	30min	60min	2h	3h	4h	5h	8h	10h	20h
9.60V	165	152	96.0	60.0	36.0	24.5	19.4	16.9	12.0	10.2	5.24
9.90V	160	148	94.1	59.1	35.8	24.3	19.3	16.8	12.0	10.2	5.23
10.2V	153	143	91.2	57.6	35.5	24.2	19.1	16.7	11.9	10.1	5.22
10.5V	147	138	89.0	56.5	35.0	24.0	19.0	16.6	11.8	10.1	5.19
10.8V	139	131	85.7	54.7	34.1	23.3	18.4	16.1	11.4	10.0	5.15


恒功率放电特性Constant power discharge characteristicsUnit:W(25℃)

F. V/TIME	10min	15min	30min	60min	2h	3h	4h	5h	8h	10h	20h
9.60V	1782	1669	1077	684	417	288	228	200	143	122	62.9
9.90V	1729	1629	1056	674	415	286	227	199	142	121	62.8
10.2V	1657	1569	1023	657	411	284	225	198	141	121	62.6
10.5V	1586	1515	998	644	405	282	223	196	140	120	62.2
10.8V	1497	1435	962	624	395	274	217	190	136	119	61.8


All mentioned values are average values

ISO9001:2008 Certificate


温度对容量影响曲线图
Effect of temperature on the capacity curve




储存特性
Storage characteristic




循环使用寿命
Life characteristics of cyclic use




温度对长期浮充使用寿命的影响
Effect of temperature on long term float life



放电特征曲线
Discharge characteristics at various rates



充电特征曲线(循环使用)
Charge characteristics for cycle use



充电方法
Charging Procedures(12V series)

使用方式 Application	Charge Voltage(V) 充电电压			最大电流 Max. Charge Current
	温度 Temperature	设置电压 Set point	允许使用范围 Allowable range	
循环使用 Cycle use	25°C	14.8	14.6 ~ 14.8	0.3C
浮充使用 Standby	25°C	13.7	13.6 ~ 13.8	0.3C

放电电流与放电电压
Discharge Current VS. Discharge Voltage

终止电压 Final Discharge Voltage V/cell	1.75V	1.70V	1.60V
放电电流 Discharge Current(A)	(A) ≤ 0.2C	0.2C < (A) < 1.0C	(A) ≥ 1.0C